

AMENDMENTS TO THE SPECIFICATION

Please amend the specification as follows:

Page 6, lines 9-24

FIG. 1 shows an example of a cigarette filter prepared in this Example. The cigarette filter 1 was prepared as follows. Two filter materials (plain filters) 2 were prepared by forming acetate having a filament fineness of 2.2 denier and a tow fineness of 40,000 denier to have a length of 10 mm, and the filter materials were wrapped with plug wrap paper 3, respectively, so as to obtain two filter sections. ~~Two~~The two filter materials 2 were arranged to have a space formed therebetween, and the two filter sections were wrapped with forming paper 5 under the state that a mixture of 30 mg of activate charcoal 41 and 30 mg of silica/alumina (trade name: Kyoward 700SN) 42 as adsorbents 4 was loaded in the space. In this case, the space was controlled to permit the adsorbents to have an apparent density of 100%.